



# THE UNITED STATES OF AMERICA

TO ALL TO WHOM THESE PRESENTS SHALL COME:

UNITED STATES DEPARTMENT OF COMMERCE

United States Patent and Trademark Office

*March 31, 2005*

**THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A FILING DATE.**

**APPLICATION NUMBER: 60/509,679**

**FILING DATE: October 08, 2003**

**RELATED PCT APPLICATION NUMBER: PCT/US04/32650**



Certified by

Under Secretary of Commerce  
for Intellectual Property  
and Director of the United States  
Patent and Trademark Office



15866 U.S. PTO

Mail Stop PROVISIONAL PATENT APPLICATION  
Commissioner for Patents  
P.O. Box 1450  
Alexandria, VA 22313-1450

PATENT  
Docket No. 12003023

22582 U.S. PTO  
60/509679



TRANSMITTAL OF PROVISIONAL APPLICATION  
PURSUANT TO 37 CFR § 1.53(c)

Application of: David Jarus

whose address is: 33587 Walker Road, Avon Lake, OH 44102

For: Nanoconcentrates Containing Polyolefin Elastomer

1. Enclosed is a new provisional patent application. It includes 10 pages of text and 0 page(s) of drawings.
2. Please charge Deposit Account No. 07-1077 in the amount of \$160.00 for the fee pursuant to 37 CFR § 1.16(k). Please credit or debit that account as needed to complete the filing of the application.
3. Please address all correspondence relating to this application to the following address:

John H. Hornickel  
PolyOne Corporation B-418  
33587 Walker Road  
Avon Lake, Ohio 44012

Registration No.  
29,393

Telephone No.  
440-930-3317

Signature

Date 8 October 2003

John H. Hornickel  
John H. Hornickel

CERTIFICATE OF EXPRESS MAILING

☒ Under 37 CFR § 1.10, I certify that this application is being deposited, on the date indicated below, with the United States Postal Service "Express Mail Post Office to Addressee" service addressed to the Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450

Express Mail Mailing Label No.

EL396969579 US

Date of Deposit

8 October 2003

Signature of Person Making Certification

John H. Hornickel

Printed Name of Person Making Certification

John H. Hornickel

## **Nanoconcentrates Containing Polyolefin Elastomer**

### **Field of Invention**

5           This application relates to polymer concentrates containing nanoclays.

### **Background of the Invention**

          Nanotechnology is an exciting new field of science. The use of  
intercalated phyllosilicates, also called smectite clays, particularly  
10   montmorillonite clays, has been recognized as valuable for reinforcing fillers.

          Nanocor, Inc. is a leader in the field of making and selling  
montmorillonite nanoclays and concentrates of them where the clays are  
exfoliated. Further technical and commercial information can be found at  
[www.nanocor.com](http://www.nanocor.com).

15           One of the polymers into which montmorillonite nanoclay concentrates  
is thermoplastic polyolefin (TPO), particularly where the polyolefin is  
polypropylene (PP).

### **Summary of the Invention**

20           One aspect of the invention is the utilization of polyolefin rubber in a  
nanoconcentrate which contains nanoclay.

          Another aspect of the present invention is a method of making the  
nanocomposite wherein the polyolefin elastomer is added downstream in an  
extruder from where the other ingredients are added.

25           An advantage of the present invention is that a balance of stiffness and  
toughness is achieved using in a TPO the nanocomposites of the present  
invention prepared according to the method of the present invention. This  
balance of stiffness and toughness is superior to those of the TPO without  
nanoconcentrates therein.

Another advantage of the present invention is that the method delays addition of the polyolefin rubber until after the nanoclay is thoroughly dispersed in the concentrate carrier, usually PP. This delay, it is believed, assures that the nanoclay present is not as likely to become intermixed within the dispersed phase of polyolefin rubber. Thus, the valuable nanoclay can increase the benefit of its properties in the final article molded from a combination of TPO and the nanoconcentrate of the present invention.

#### Embodiments of the Invention

10 TPO's are commercially available from such multi-national sources as Basell Polyolefins. TPO's can have a variety of properties, ranging from rigid to flexible to impact-modified polyolefin copolymers along a continuum known to those skilled in the art. The final use of an article made from TPO benefits from these tailored properties.

15 Nanoclay is a clay from the smectite family. Smectites have a unique morphology, featuring one dimension in the nanometer range. Montmorillonite clay is the most common member of the smectite clay family. The montmorillonite clay particle is often called a platelet, meaning a sheet-like structure where the dimensions in two directions far exceed the particle's thickness.

20 Nanoclay becomes commercially significant if intercalated with an intercalant. An intercalate is a clay-chemical complex wherein the clay gallery spacing has increased, due to the process of surface modification by an intercalant. Under the proper conditions of temperature and shear, an intercalate is capable of exfoliating in a resin matrix. An intercalant is an organic or semi-organic chemical capable of entering the montmorillonite clay gallery and bonding to the surface. Exfoliation describes a dispersion of a surface treated nanoclay in a plastic matrix.

25 In exfoliated form, nanoclay platelets have a flexible sheet-type structure which is remarkable for its very small size, especially the thickness of the sheet.

The length and breadth of the particles range from 1.5  $\mu\text{m}$  down to a few tenths of a micrometer. However, the thickness is astoundingly small, measuring only about a nanometer (a billionth of a meter). These dimensions result in extremely high average aspect ratios (75-500). Moreover, the miniscule size and thickness mean that a single gram contains over a million individual particles.

Nanocomposites are the combination of the surface treated nanoclay and the plastic matrix. In polymer compounding, a nanocomposite is a very convenient means of delivery of the nanoclay into the ultimate compound, provided that the plastic matrix is compatible with the principal polymer resin components of the compounds. In such manner, nanocomposites are available in concentrates, masterbatches, and compounds from Nanocor, Inc. of Arlington Heights, Illinois ([www.nanocor.com](http://www.nanocor.com)) and PolyOne Corporation of Avon Lake, Ohio ([www.polyone.com](http://www.polyone.com)) in a variety of nanocomposites.

Nanocomposites offer flame-retardancy properties because such nanocomposite formulations burn at a noticeably reduced burning rate and a hard char forms on the surface. They also exhibit minimum dripping and fire sparkling.

When using Nanocor produced nanoclay, the amount of this additive in concentrate form can range from about 2 weight percent to about 50 weight percent, and preferably between about 3 and about 20 weight percent of the total compound. Upon addition to the compound, the intercalated nanoclay exfoliates with the addition of compatibilizers known to those skilled in the art. In a preferred embodiment, the compatibilizer is a grafted maleic anhydride such as disclosed in U.S. Pat. No. 5,717,500 (Karande et al.).

The preparation of nanoconcentrates uses extrusion mixing equipment known to those skilled in the art. But the present invention departs from convention in that the concentrate differs from the TPO to which is to be mixed. Conventionally, the concentrate is made by mixing TPO and nanoclay, and

optionally a compatibilizing dispersion agent such as maleated polypropylene (PP-g-MAH).

In the present invention, the TPO is not used in forming the concentrate. Rather, the constituents of the TPO, PP and an elastomer, particularly a polyolefin elastomer, are added separately and at different locations in the extruder. More specifically, the polyolefin elastomer is added downstream of the other ingredients, which gives the nanoclay and its optional dispersion agent both more time and less interference in dispersing completely within the polypropylene carrier.

Preferably, the mixing equipment is a co-rotating twin-screw extruder commercially available from Werner-Pfleiderer. The extruder should be capable of screw speeds ranging from about 50 to about 12,000 rpm. The temperature profile from the barrel number two to the die should range from about 170°C to about 270°C, and preferably from around 200°C for this nanoconcentrate. The nanoconcentrate can be pelletized for later use.

Polyolefin elastomers or rubber in the present invention are used for the separate mixing reason described above, instead of an already blended TPO. Any suitable polyolefin elastomer can be used. For example, polybutadiene rubber, ethylene-propylene-diene rubber (EPDM), ethylene-octene copolymers, and other elastomers are useful. Non-limiting examples of such elastomers are those commercially available from multinational companies such as Bayer, Dupont-Dow Elastomers, Uniroyal Chemical, ExxonMobil, and others. ENGAGE™ 8180, ENGAGE™ 8842, and other ENGAGE™ polyolefin elastomers are especially preferred ethylene-octene copolymers available from DuPont Dow Elastomers LLC of Wilmington, DE that function well as impact modifiers for nanoconcentrates of the invention.

Nanoconcentrate pellets of the present invention can be mixed with TPO's to form articles benefiting from a balance of stiffness and toughness properties introduced by the nanoclays therein. The nanoconcentrate can be

diluted or "let-down" in any ratio that one skilled in the art desires to yield as a final nanoclay concentration in the article.

One way of dilution is with a twin-screw extruder from any number of sources or a continuous mixer from Farrel. Further information on this  
5 technique is found at [www.nanocor.com/tech\\_sheets/P806.pdf](http://www.nanocor.com/tech_sheets/P806.pdf) which describes let-down of conventional nanoconcentrates into TPO's.

Another way of dilution is mixing the nanoconcentrate at the point of molding the final article. The mixing inlet for any type of molding machine can be sufficient to disperse the nanoconcentrate of the present invention into the  
10 TPO. This is an efficient way to introduce a more expensive concentrate into a final molded product, based on working capital requirements of raw material inventory, because the nanoconcentrate arrives just-in-time.

#### Usefulness of the Invention

15 Final molded articles made from TPO are more valuable because nanoclays provide increased stiffness and toughness. Such molded articles can be made into any number of shapes, among them, automobile parts, large appliance parts, and the like.

Further explanation of the invention is found in the following examples.  
20

#### Examples

Nanoclay-containing concentrates were prepared according to the recipes and commercial sources stated in Table 1 and the mixing conditions stated in Table 2. The concentration of nanoclay and dispersion agent were kept  
25 constant with the concentration of polyolefin copolymer rubber being varied.

<b>Table 1</b>				
<b>Concentrate Recipes for Use in TPO</b>				
<b>Ingredient Wt. %</b>	<b>1</b>	<b>2</b>	<b>3</b>	<b>4</b>
Nanoclay	40	40	40	40
PP-g-MAH	10	10	10	10
EO Copolymer Rubber	15	10	5	0

Table 1				
PP	35	40	45	50
Commercial Sources				
Ingredient and Use		Source	Brand(s)	
Nanoclay to enhance stiffness		Nanocor	I44p	
Ethylene-Octene Copolymer to modify impact		DuPont-Dow	EG8180	
PP-g-MAH (maleated polypropylene) to disperse nanoclay		Crompton	PolyBond PBX5104	
PP (polypropylene) to serve as concentrate carrier				
TPO (thermoplastic polyolefin)		Basell	CA387; Adflex KS311P; and Pro-Fax SG702	

Table 2				
Concentrate Making Conditions				
Example	1	2	3	4
Concentrate Mixing Equipment	Werner & Pfleiderer ZSK 25 co-rotating twin screw extruder			
Concentrate Mixing Temperature	200°C			
Concentrate Mixing Speed	1100 rpm			
Order of Addition	All Ingredients except Ethylene-Octene Copolymer are added together, with EO Copolymer added downstream, i.e., after thorough dispersion of nanoclay and dispersion agent in carrier			

After the concentrates 1-4 were made, they were mixed into three different TPO's to simulate the addition of concentrate just prior to molding of the TPO into a useful article.

Table 3 shows the amount of dilution, also known as let-down, along with the test results for stiffness and toughness of the final article.

Table 3				
TPO Compounds				
Example	Concentrate	Wt. Percent	TPO	Wt. Percent
Comp. A	--	--	CA387P	100%
5	1	20%	CA387P	80%
6	2	20%	CA387P	80%
7	3	20%	CA387P	80%
8	4	20%	CA387P	80%
Comp.B	--	--	Pro-Fax SG702	100%
9	1	20%	Pro-Fax SG702	80%
10	2	20%	Pro-Fax SG702	80%
11	3	20%	Pro-Fax SG702	80%
12	4	20%	Pro-Fax SG702	80%
Comp. C	--	--	Adflex KS311P	100%



13	1	20%	Adflex KS311P		80%			
14	2	20%	Adflex KS311P		80%			
15	3	20%	Adflex KS311P		80%			
16	4	20%	Adflex KS311P		80%			
17	2	10%	Adflex KS311P		90%			
Example	ASTM D790 (PSI)		ASTM D3837 (Joules)					
	Flex. Mod.	Stress at Yield	Inst. Impact Room Temp. Peak    Total		Inst. Impact 0°C Peak    Total		Inst. Impact -30°C Peak    Total	
Comp. A	120000	3380	16.7	30.7			24.9	45
5	149000	3540	16.8	30.5			24.6	39.3
6	157000	3740	16.6	30.2			22.6	27
7	158000	3850	16.6	29.7			13.8	14.4
8	179000	4110	16.5	28.7			3.9	4.9
Comp. B	155000	4770	18.8	33.8	22.4	41.3		
9	233000	5530	20.1	31.1	24.1	37.4		
10	239000	5650	21.1	30.3	18.5	22.5		
11	244000	5720	20.6	28.5				
12	258000	5980	20.6	24.3	11.5	12.1		
Comp. C	78400	2530	13.8	25				
13	123000	3040	16.1	26.9				
14	130000	3220	15.7	26.4				
15	133000	3330	15.1	26.2				
16	149000	3540	15.4	25.4				
17	109000	3010	15.2	26.4				

Table 3 shows that Examples 5-8, 9-12, and 13-16 (each containing 8 wt. percent nanoclay) consistently outperform the Comparative Examples A, B, and C, respectively, in respect of Flexural Modulus and Stress at Yield.

- 5 Because each of the Comparative Examples are different types of TPO (A is a rigid TPO; B is an impact copolymer; and C is a flexible TPO), assessment of instrument impact performance is more complex. All of Examples 5-16 exhibit ductility by comparing the peak vs. total instrument impact values. As
- 10 polyolefin copolymer content decreases, instrument impact performance at the various operational temperatures also decreases. Therefore, the balance of stiffness and toughness is found preferably in Examples 5, 9, and 13.

Examples 14 and 17 compare the amount of nanoclay present in the TPO Compounds of the same ingredients, with Example 14 containing 8% nanoclay and Example 17 containing 4%. Along with Comparative Example C,

a trend line can be established from 0 to 4 to 8 weight percent, with increased stiffness along that line.

The invention is not limited to the above embodiments. The claims follow.

What is claimed is:

1. A method of making a nanocomposite of carrier, nanoclay, polyolefin elastomer and optional nanoclay dispersion agent, comprising the steps of

(a) adding the carrier, nanoclay, and optional nanoclay dispersion agent  
5 to an extruder; and

(b) adding the polyolefin elastomer downstream from where the carrier, nanoclay, and optional nanoclay dispersion agent were added.

## **Nanoconcentrates Containing Polyolefin Elastomer**

### **Abstract**

5 A concentrate of nanoclay, polyolefin carrier, and polyolefin elastomer is disclosed, optionally also containing a dispersion agent for the nanoclay. The nanocomposite is prepared for use with thermoplastic polyolefins (TPO's). The polyolefin elastomer, preferably an ethylene-octene copolymer, is added into a mixing extruder downstream of the other ingredients. The nanoconcentrate contributes increased stiffness and toughness to a TPO, which can be used form molded articles such as automotive parts.

# Document made available under the Patent Cooperation Treaty (PCT)

International application number: PCT/US04/032650

International filing date: 01 October 2004 (01.10.2004)

Document type: Certified copy of priority document

Document details: Country/Office: US  
Number: 60/509,679  
Filing date: 08 October 2003 (08.10.2003)

Date of receipt at the International Bureau: 18 April 2005 (18.04.2005)

Remark: Priority document submitted or transmitted to the International Bureau in compliance with Rule 17.1(a) or (b)



World Intellectual Property Organization (WIPO) - Geneva, Switzerland  
Organisation Mondiale de la Propriété Intellectuelle (OMPI) - Genève, Suisse